

Norbord Durastrand[®] LSL & OSL
Norbord Inc.

PR-L260

Revised December 4, 2018

Products: Norbord Durastrand[®] 1.7E LSL, 1.5E OSL, 1.3E OSL, and 0.8E OSL
Norbord Inc., 1 Toronto Street, Suite 600, Toronto, Ontario M5C 2W4, Canada
(416) 365-0705
www.norbord.com

1. Basis of the product report:
 - 2018 and 2015 International Building Code (IBC): Sections 104.11 Alternative materials and 2303.1.10 Structural composite lumber
 - 2012 IBC: Sections 104.11 Alternative materials and 2303.1.9 Structural composite lumber
 - 2018, 2015, and 2012 International Residential Code (IRC): Section R104.11 Alternative materials
 - ASTM D5456-14b, D5456-13, and D5456-09 recognized by the 2018 IBC and IRC, 2015 IBC and IRC, and 2012 IBC and IRC, respectively
 - APA Reports T99Q-22, T2003Q-25, T2006P-59, T2006P-60, T2006P-61, T2006P-62, T2006P-67, T2006P-69, T2006P-91, T2007P-53, T2008P-87, T2008P-88, T2011P-21, T2012P-44, and T2018P-08A, and other qualification data and engineering analyses
2. Product description:

Norbord Durastrand LSL and OSL are made with strands of various species and strand classifications in accordance with the in-plant manufacturing standard approved by APA. Norbord Durastrand 1.7E LSL, 1.5E OSL and 1.3E OSL are available in thicknesses from 1-3/4 to 5-1/4 inches, widths up to 24 inches, and lengths up to 48 feet. Norbord Durastrand 0.8E OSL is available in a thickness of 1-1/4 inches, widths up to 24 inches, and lengths up to 24 feet.
3. Design properties:

Table 1 lists the design properties, Table 2 lists the equivalent specific gravities for fastener design for Norbord Durastrand LSL and OSL, Table 3 lists the allowable loads for rim boards, and Table 4 lists the allowable nail spacing. The allowable spans for Norbord Durastrand LSL and OSL shall be engineered using the information provided in this report.
4. Product installation:

Norbord Durastrand LSL and OSL shall be installed in accordance with the engineering drawing approved by the engineer of record. Permissible details and allowable hole sizes shall be in accordance with the engineering drawing. When used as rim boards, Norbord Durastrand LSL and OSL shall be permitted to be constructed in accordance with the *Rim Board Hole Specifications* provided by *APA Performance Rated I-Joists, Form Z725* (www.apawood.org/resource-library).
5. Fire-rated assemblies:

The provisions of 2018 and 2015 IBC Section 722 Calculated fire resistance and 2012 IBC Section 722.6.3 Design of fire-resistant exposed wood members shall be applicable to Norbord Durastrand LSL. Fire-rated assemblies shall be constructed in accordance with the recommendations provided by *APA Design/Construction Guide: Fire-Rated Systems, Form W305* (see link above), and the manufacturer.
6. Limitations:
 - a) Norbord Durastrand LSL and OSL shall be designed in accordance with the applicable code using the design properties specified in this report.

- b) Norbord Durastrand LSL and OSL are limited to dry service conditions where the average equilibrium moisture content of sawn lumber is less than 16 percent.
 - c) Norbord Durastrand LSL and OSL is produced by Norbord Inc. at Norbord's facilities in Grande Prairie, Alberta, and 100 Mile House, British Columbia, under a quality assurance program audited by APA.
 - d) This report is subject to re-examination in one year.
7. Identification:
Norbord Durastrand LSL and OSL described in this report are identified by a label bearing the manufacturer's name and/or trademark (Norbord), the APA assigned plant number (454 for the Grande Prairie Plant, and 445 for the 100 Mile House Plant), the product grade, the APA logo, the report number PR-L260, and a means of identifying the date of manufacture.

Table 1. Design Properties (Allowable Stress Design) for Norbord Durastrand LSL and OSL^(a)

GRADE	E ^(b) (10 ⁶ psi)	AXIAL (psi)		JOIST/BEAM EDGE LOADING ^(c) (psi)			PLANK FACE LOADING (psi)		
		F _t ^(d,e)	F _c	F _b ^(f,g,h)	F _v	F _{c⊥}	F _b ^(f)	F _v	F _{c⊥}
1.7E	1.7	2,050	2,050	2,150	400	1,200	2,800	150	325
1.5E	1.5	1,775	1,775	1,750	400	1,150	2,550	130	325
1.3E	1.3	1,300	1,300	1,625	350	1,150	2,000	115	285
0.8E	0.8	680	1,100	1,130	355	1,415	-	-	-

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa

- (a) The tabulated values are allowable design values for normal duration of load. All values, except for E and F_{c⊥}, are permitted to be adjusted for other load durations as permitted by the code. The design stresses are limited to conditions in which the maximum moisture content of sawn lumber is less than 16 percent.
- (b) For uniformly loaded simple-span beams on edge, deflection is calculated as follows:

$$\delta = \frac{270 wL^4}{Ebh^3} + \frac{28.8 wL^2}{Ebh}$$

For uniformly loaded simple-span beams on face, deflection is calculated as follows:

$$\delta = \frac{270 wL^4}{Ebh^3} + \frac{86.0 wL^2}{Ebh}$$

Where: δ = Estimated deflection, inches, w = uniform load, plf
 L = span, feet, E = tabulated modulus of elasticity, psi
 b = beam width, inches, and h = beam depth, inches

- (c) Joist = load parallel to glueline.
- (d) F_t value for 0.8E OS� is applicable to lengths up to 24 feet.
- (e) The tabulated values are based on a reference length of 4 feet. For other lengths, the allowable tensile stress shall be modified by (4/L)^{1/8}, where L = length in feet. For lengths less than 4 feet, use the allowable tension stresses in Table 1 unadjusted.
- (f) Tabulated flexural stress (F_b) may be increased by 4 percent when the member qualifies as a repetitive member as defined in the NDS.
- (g) Edgewise F_b value for 0.8E OS� is applicable to a 16-inch depth or less.
- (h) The tabulated values are based on a reference depth of 12 inches. For other depths, when loaded edgewise, the allowable bending stress (F_b) shall be modified by (12/d)^{1/4}, as shown in the following table. For depths less than 2-1/2 inches, the factor for the 2-1/2-inch depth shall be used.

Depth (in.)	2-1/2	5-1/2	7-1/4	9-1/4	11-1/4	12	16	18	20	24
Multiply by	1.48	1.22	1.13	1.07	1.02	1.0	0.93	0.90	0.88	0.84

Table 2. Fastener Design for Norbord Durastrand LSL and OSL

GRADE	EQUIVALENT SPECIFIC GRAVITY (S.G.)						LATERAL LOAD ^(a) (pounds)
	NAILS				BOLTS		LAG BOLT
	Withdrawal Load		Lateral Load		Lateral Load		Installed in Face
	Installed in Edge	Installed in Face	Installed in Edge	Installed in Face	Installed in Face		
Parallel to Grain					Perpendicular to Grain		
1.7E	Red pine (0.44)	Mixed southern pine (0.51)	Douglas fir-larch North (0.49)	Red maple (0.61)	Mixed southern pine (0.51)	Red oak (0.66)	400
1.5E	Red pine (0.44)	Douglas fir-larch (0.50)	Hem-fir North (0.46)	Mixed maple (0.55)	Douglas fir-larch North (0.49)	Red maple (0.60)	400
1.3E	Red pine (0.44)	Douglas fir-larch North (0.49)	Eastern hemlock (0.41)	Mixed southern pine (0.51)	Englemann spruce-lodgepole pine (0.38)	Southern pine (0.55)	400
0.8E	Northern white cedar (0.32)	Hem-fir (0.43)	-	Douglas fir-larch (0.50)	Northern white cedar (0.32)	Red maple (0.61)	400

For SI: 1 inch = 25.4 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa

(a) The lateral capacity is for a 1/2 -inch diameter lag bolt installed into the face of Durastrand® based on 1-1/2-inch-thick spruce-pine-fir side member and 1/2-inch-thick sheathing with a full penetration of the Durastrand® by the lag bolt.

Table 3. Norbord Durastrand Allowable Loads for Rim Board Applications

GRADE	Thickness (in.)	VERTICAL LOAD ^(a)				LATERAL CAPACITY ^(c,d,e,f,g) (pounds per foot)	
		Uniform ^(b) (pounds per foot)		Concentrated (pounds)		Nails Spaced at 6 in. o.c.	Nails Spaced at 4 in. o.c.
		Depths ≤ 16 in.	24 in. ≥ Depth > 16 in.	Depth ≤ 16 in.	24 in. ≥ Depth > 16 in.		
1.3E	1-3/4	7,000	4,350	5,200	5,200	240	--
0.8E	1-1/4	5,700	3,500	5,900	5,500	240	330

For SI: 1 inch = 25.4 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa

- (a) The vertical load capacities are based on the normal load duration (10 years), which are not permitted to be increased for any shorter load durations.
- (b) The allowable vertical uniform load capacity is based on the strength of the rim board and may need to be reduced based on the bearing capacity of the supporting wall plate.
- (c) The tabulated lateral load capacity is based on the short-term load duration (10 minutes).
- (d) Durastrand® may be substituted for solid-sawn framing in horizontal wood diaphragms as shown in Tables 4.2A and Table 4.2C of the 2015 ANSI/AWC Special Design Provisions for Wind and Seismic (SDPWS) (for 2018 and 2015 IBC) and 2008 SDPWS (for 2012 IBC), provided the maximum allowable shear values for the diaphragms are limited to the allowable lateral capacity noted in this table.
- (e) Toe-nailed connections are not limited by the 150 lbf/ft allowable lateral load capacity noted for Seismic Design Categories D, E, and F in Section 4.1.7 of the ANSI/AWC SDPWS.
- (f) 8d common nails shall be used to connect the floor sheathing to the Durastrand® and to connect the Durastrand® to the sill plate (toe nail). The nails shall be spaced as noted in the table. Two 8d nails are required to connect each floor joist to the sill plate, and two 8d nails are required to connect the Durastrand® to the end of each floor joist.
- (g) See Table 4 for minimum nail spacing requirements.

Table 4. Minimum Allowable Nail Spacings for Norbord Durastrand LSL and OSL

CONNECTOR SIZE	NAILS INSTALLED IN THE NARROW FACE ^(a)		NAILS INSTALLED IN THE WIDE FACE ^(b)	
	ON-CENTER SPACING (in.)	END DISTANCE (in.)	ON-CENTER SPACING (in.)	END DISTANCE (in.)
8d box and common nail or smaller	3	2	1	1/2
10d box and common nail	4	2	1	1/2
16d box nail	4	2	1	1/2
16d sinker (12d common) nail	4	2	1	1/2
16d common nail	5	2-1/2	1	7/8

For SI: 1 inch = 25.4 mm

- (a) Multiple rows of nails are allowed, with a minimum of 1/2-inch spacing between rows and when applied to the edge. Rows are to be equal distance from centerline.
- (b) In general, the minimum on-center spacing permitted for nails installed in the wide face of Durastrand is the same as that permitted by the applicable code for solid-sawn lumber.

APA – *The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
 HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466
 Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
 (253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.