



Murphy LVL Scaffold Plank
Murphy Engineered Wood Division

PR-L312
Revised April 23, 2023

Products 2350F_b-2.0E Murphy LVL Scaffold Planks
Murphy Engineered Wood Division, 412 West Central, Sutherlin, Oregon 97479
(541) 459-4545
www.murphyplywood.com/engineered/

1. Basis of the product report:
 - ASTM D5456-21e1, Standard Specification for Evaluation of Structural Composite Lumber Products
 - ANSI/ASSP A10.8-2019, Scaffolding Safety Requirements
 - APA Reports T2013P-01, T2014P-50, and T2015P-07A, and other qualification data
2. Product description:

Murphy laminated veneer lumber (LVL) Scaffold Planks are made with wood veneers laminated with grain parallel to the length of the member in accordance with the in-plant manufacturing standard approved by APA. Murphy LVL Scaffold Planks are available in 1-1/2 inches in thickness, and a range of widths and lengths. Refer to the manufacturer's technical guide (https://murphyplywood.com/pdfs/engineered/Murphy_Scaffold_Plank_Technical_Guide.pdf) and a local Murphy LVL distributor for product availability.
3. Design properties:

Table 1 lists the design properties for Murphy LVL Scaffold Planks. Table 2 lists the wet service factors, which shall be applied when the average moisture content of the planks is 16% or more. The allowable loads for Murphy LVL Scaffold Planks shall be in accordance with the recommendations provided by the manufacturer (see link above). Murphy LVL Scaffold Planks shall be used based on information provided in this report and the recommendations provided by the manufacturer.
4. Product installation:

Murphy LVL Scaffold Planks shall be installed in accordance with the recommendations provided by the manufacturer (see link above) and OSHA (www.osha.gov).
5. Storage, handling, inspection, and evaluation:

The storage and handling of Murphy LVL Scaffold Planks shall be in accordance with the recommendations provided by the manufacturer (see link above). Murphy LVL Scaffold Planks shall be inspected by a qualified person to ensure the products are in good condition prior to use. Products with defects, such as and not limited to end or edge splits, dents or gouges, face breaks, discoloration, odor, or decay, shall be removed from service.
6. Limitations:
 - a) Murphy LVL Scaffold Planks shall be designed in accordance with ANSI/ASSP A10.8 using the design properties specified in this report.
 - b) Murphy LVL Scaffold Planks are intended primarily for use in dry service conditions where the average moisture content of the plank is less than 16%. When Murphy LVL Scaffold Planks are used where the average moisture content of the plank will be 16% or more, design values shall be multiplied by the appropriate wet service factors as shown in Table 2.
 - c) Murphy LVL Scaffold Planks shall not be used as a structural member, such as beam or header, in wood framed construction.

- d) Murphy LVL Scaffold Planks are produced at the Murphy Engineered Wood Division facilities in Sutherlin, Oregon under a quality assurance program audited by APA.
- e) This report is subject to re-examination in one year.

7. Identification:

Murphy LVL Scaffold Planks described in this report are identified by a label bearing the manufacturer's name (Murphy Engineered Wood Division) and/or trademark, the APA assigned plant number (1089), the scaffold plank grade (2.0E), the APA logo, and a means of identifying the date of manufacture.

Table 1. Murphy LVL Scaffold Plank Flatwise Design Properties (Allowable Stress Design)^(a)

Scaffold Design Property	Design Stress (psi)
	2.0E LVL Scaffold Planks
Bending (F_b) in the plank orientation	2,350
Modulus of Elasticity (E) in the plank orientation	2,000,000
Longitudinal shear (F_v) in the plank orientation	150

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa

^(a) The tabulated values are design values for normal duration of load and shall not be increased for other load durations. The design values are limited to conditions where the average moisture content of the plank is less than 16%. When Murphy LVL Scaffold Planks are used where the average moisture content of the plank will be 16% or more, design values shall be multiplied by the appropriate wet service factors listed in Table 2.

Table 2. Wet Service Factors (for plank moisture content of 16% or more)

Bending (F_b)	Modulus of Elasticity (E)	Longitudinal shear (F_v)
0.83	0.92	0.70

APA – The Engineered Wood Association is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, Validation Entity, and Product Evaluation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. ▪ Tacoma, Washington 98466
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 ▪ *E-mail Address:* help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.