

West Fraser Proprietary OSB Facers for SIPs
West Fraser Timber Co. Ltd.

PR-N612
Revised April 19, 2024

Product: West Fraser 7/16 Proprietary OSB Facers for SIPs
West Fraser Timber Co. Ltd., 885 West Georgia Street, Suite 1500, Vancouver, British Columbia, V6C 3E8, Canada
(604) 895-2700
osb.westfraser.com

- Basis of the product report:
 - 2021, 2018, and 2015 International Residential Code (IRC): Section R610 Structural Insulated Panel Wall Construction
 - 2012 IRC: Section R613 Structural Insulated Panel Wall Construction
 - DOC PS 2-18, Performance Standard for Wood Structural Panels
 - ANSI/APA PRS 610.1-2023, Standard for Performance-Rated Structural Insulated Panels in Wall Applications
 - APA Reports T2010P-44, T2020P-03, and T2023P-48, and other qualification data
- Product description:

West Fraser proprietary OSB facers are 7/16 Performance Category panel sheathing that can be used as facers of structural insulated panels (SIPs) when manufactured to a proprietary mill specification documented in the in-plant manufacturing standard and approved by APA. In addition to the requirements for PS 2, the proprietary OSB facers meet the properties shown in Table 3 of this report, which are equal to or higher than those specified in Table 2 of ANSI/APA PRS 610.1 as referenced in the 2021 and 2018 IRC, Table R610.3.2 of the 2015 IRC, and Table R613.3.2 of the 2012 IRC. The proprietary OSB facers are also listed in APA Product Report PR-N610. Products may be treated with *Borogard*[®] ZB (registered trademark of U.S. Borax; an EPA-registered zinc borate preservative), as recognized in APA Product Report PR-N213. The efficacy of the preservative treatment is outside the scope of this report and the APA certification program. The properties of the proprietary OSB facers are quality-controlled on an on-going basis.
- Minimum panel properties:

West Fraser proprietary OSB facers meet the properties specified in Table 1.

Table 1. Minimum Properties for West Fraser Proprietary OSB Facers ^(a)

Thickness (in.)	Flatwise Stiffness ^(b) (lbf-in. ² /ft)		Flatwise Strength ^(c) (lbf-in./ft)		Tension ^(c) (lbf/ft)		Density ^(d) (pcf)
	Along	Across	Along	Across	Along	Across	
7/16	55,600	27,100	1,040	870	7,450	6,500	35

For SI: 1 lbf-in.²/ft = 9.415 x 10⁻⁶ kN-m²/m, 1 lbf-in./ft = 3.707 x 10⁻⁴ kN-m/m, 1 lbf/ft = 0.0146 N/mm, 1 pcf = 16.018 kg/m³

^(a) Tabulated values are test values, which are not intended for use in design.
^(b) Mean test value shall be in accordance with Section 7.6 of PS 2.
^(c) Characteristic test value (5th percentile with 75% confidence).
^(d) Mean density value shall be based on oven-dry weight and oven-dry volume in accordance with Method A of ASTM D2395.

4. Limitations:

- a) The properties listed in Table 1 are minimum test values and related only to the West Fraser proprietary OSB facers. Design values for SIPs shall be provided by the SIP manufacturer.
- b) West Fraser proprietary OSB facers are limited to dry service conditions where the average equilibrium moisture content of sawn lumber is less than 16%.
- c) West Fraser proprietary OSB facers are produced by West Fraser Timber Co. Ltd. at the facilities in Barwick, ON, Guntown, MS, and Lanett, AL, under a quality assurance program audited by APA. The efficacy of the preservative treatment is outside the scope of this report and the APA certification program.
- d) This report is subject to re-examination in one year.

5. Identification:

West Fraser proprietary OSB facers recognized in this report are identified by a label bearing the manufacturer's name and/or trademark (West Fraser), the APA assigned plant number (498 for Barwick, ON, 502 for Guntown, MS, and 503 for Lanett, AL), the product Performance Category (7/16), the Span Rating (24/16), the Exposure Rating, the APA logo, the report number PR-N612, and a means of identifying the date of manufacture.

APA – *The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, Validation Entity, and Product Evaluation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466
Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. No warranties, express or implied, including as to fitness for a particular purpose, are made regarding this report. Neither APA nor its members shall be liable, or assume any legal liability or responsibility, for damages, direct or indirect, arising from the use, application of, and/or reference to opinions, findings, conclusions or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.