

**Power Preserved Glulam<sup>®</sup>** **PR-L282**  
**Beams and Columns**  
**Anthony Forest Products/Canfor** Revised May 24, 2017

Products: Power Preserved Glulam<sup>®</sup> Beams and Columns  
Anthony Forest Products Company, LLC, 309 N. Washington, El Dorado, AR 71730  
(800) 221-2326  
[www.anthonyforest.com](http://www.anthonyforest.com)

1. Basis of the product report:
  - 2015, 2012, and 2009 International Building Code (IBC): Sections 104.11 Alternative materials and 2303.1.3 Structural glued laminated timber
  - 2015 International Residential Code (IRC): Sections R104.11 Alternative materials, and R502.1.3, R602.1.3, and R802.1.2 Structural glued laminated timber
  - 2012 and 2009 IRC: Sections R104.11 Alternative materials, and R502.1.5, R602.1.2, and R802.1.4 Structural glued laminated timber
  - ASTM D3737-12, D3737-08, and D3737-07 recognized by the 2015 IBC and IRC, 2012 IBC and IRC, and 2009 IBC and IRC, respectively
  - ANSI A190.1-2012 and ANSI/AITC A190.1-2007 recognized by the 2015 IBC and IRC, and 2012 IBC and IRC and 2009 IBC and IRC, respectively
  - AWPA U1-14, U1-11, and U1-07 recognized by the 2015, 2012 and 2009 IBC and IRC, respectively, and AWPA U1-16
2. Product description:

Power Preserved Glulam Beams are used as beams, headers, rafters, or purlins, and are manufactured with EWS 24F-V5M1/SP balanced layup combination in accordance with ANSI A190.1. Power Preserved Columns are manufactured with Combination #50 layup in accordance with ANSI A190.1. Power Preserved Glulam Beams are treated with Cop-Guard<sup>®</sup> (CuN) at 0.04 pcf or Clear-Guard<sup>™</sup> (IPBC/PER) at 0.055 pcf for above ground use by Hoover Treated Wood Products, Inc. ([www.frtw.com](http://www.frtw.com)) after manufacturing. Power Preserved Columns are treated with Cop-Guard<sup>®</sup> at 0.075 pcf. The efficacy of the preservative treatment, and post-treatment inspection and quality assurance of the treatment are outside the scope of this report and the APA certification program. The adhesive used in Power Preserved Glulam Beams and Columns, as trademarked by APA, conforms to wet-use requirements of ASTM D2559.
3. Design properties:

Table 1 lists the design properties for Power Preserved Glulam Beams. The allowable spans for Power Preserved Glulam Beams shall be in accordance with the recommendations provided by the manufacturer ([www.anthonyforest.com/pdfs/afp-brochure.pdf](http://www.anthonyforest.com/pdfs/afp-brochure.pdf)) and EWS Data File: *Glued Laminated Beam Design Tables*, Form S475 ([www.apawood.org/resource-library](http://www.apawood.org/resource-library)), as applicable. Table 2 lists the design properties for Power Preserved Glulam Columns. The allowable loads for Power Preserved Columns shall be in accordance with the recommendations provided by the manufacturer ([www.anthonyforest.com/assets/pdf/power-column-flyer.pdf](http://www.anthonyforest.com/assets/pdf/power-column-flyer.pdf)), and EWS Data File: *Design of Structural Glued Laminated Timber Columns*, Form Y240 (see link above), as applicable.
4. Product installation:

Power Preserved Glulam Beams and Columns shall be installed in accordance with the recommendations provided by the manufacturer and EWS Technical Notes: *Glulam Connection Details*, Form T300, and *Preservative Treatment of Glued Laminated Timber*, Form S580 (see link above). Permissible field notching and drilling shall be in accordance

with the recommendations provided by the manufacturer and EWS Technical Note: *Field Notching and Drilling of Glued Laminated Timber Beams*, Form S560 (see link above).

The American Wood Protection Association (AWPA) U1 Standard Specification F permits glulam members treated with Cop-Guard® (CuN) at a retention level of 0.04 pcf and Clear-Guard™ (IPBC/PER) at 0.055 pcf for use in AWPA use categories UC3A and UC3B for above ground applications. AWPA U1 Standard Specification F permits glulam members treated with Cop-Guard® (CuN) at a retention level of 0.075 pcf to be used in AWPA use categories UC4B and UC4C for ground contact applications.

5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer and APA *Fire-Rated Systems*, Form W305 (see link above). For one- or two-hour rated glulam beams, Power Preserved Glulam Beams and Columns shall be constructed in accordance with ANSI A190.1 and designed in accordance with the recommendations provided by the manufacturer and EWS Technical Note: *Calculating Fire Resistance of Glulam Beams and Columns*, Form Y245 (see link above) or *National Design Specification (NDS)*, available from American Wood Council ([www.awc.org/codes-standards/publications/nds-2015](http://www.awc.org/codes-standards/publications/nds-2015)).

6. Limitations:

- a) Power Preserved Glulam Beams and Columns shall be designed in accordance with the code using the design properties specified in this report.
- b) Power Preserved Glulam Beams and Columns shall have a minimum depth of 4 and 2 laminations, respectively.
- c) Power Preserved Glulam Beams treated with Cop-Guard® at 0.04 pcf and Clear-Guard™ at 0.055 pcf retention are permitted for above ground use and shall not be used in direct ground contact, water or marine applications. Power Preserved Glulam Beams treated with Clear-Guard™ shall not be installed in interior applications until the preservative solvents have been completely volatilized. Power Preserved Glulam beams treated with Cop-Guard™ shall not be installed in interior applications.
- d) Power Preserved Glulam Columns treated with Cop-Guard® at 0.075 pcf retention is permitted for use in ground contact but shall not be used in direct water or marine applications. Power Preserved Glulam Columns treated with Cop-Guard™ shall not be installed in interior applications.
- e) Power Preserved Glulam Beams and Columns are produced at Anthony Forest Products Company, LLC, El Dorado, AR, under a quality assurance program audited by APA prior to treatment. The efficacy of the treatment and overall post-treatment inspection and quality assurance program is certified by the treating company and third-party inspection provided by Timber Products Inspection (TPI).
- f) This report is subject to re-examination in one year.

7. Identification:

Power Preserved Glulam Beams and Columns described in this report are identified by a label bearing the manufacturer's name (Anthony Forest Products Company, LLC) and/or trademark, the APA assigned plant number (1079 for El Dorado, AR), the product standard (ANSI A190.1), the APA logo, the report number PR-L282, the preservative treatment by Hoover, the retention level in pcf, the AWPA use category and a means of identifying the date of manufacture.

Table 1. Design Values for Power Preserved Glulam Beams for Normal Duration of Load <sup>(1,2)</sup>

Symbol	Species Outer/Core <sup>(3)</sup> (Bal or Unbal <sup>(4)</sup> )	Bending About X-X Axis (Loaded Perpendicular to Wide Faces of Laminations)							Bending About Y-Y Axis (Loaded Parallel to Wide Faces of Laminations)					Axially Loaded		Fasteners			
		Extreme Fiber in Bending <sup>(5)</sup>		Compression Perpendicular to Grain		Shear Parallel to Grain <sup>(6)</sup>	Modulus of Elasticity <sup>(7)</sup>			Extreme Fiber in Bending <sup>(8)</sup>	Comp. Perpen-dicular to Grain	Shear Parallel to Grain <sup>(6)</sup>	Modulus of Elasticity <sup>(7)</sup>			Tension Parallel to Grain	Comp. Parallel to Grain	Specific Gravity for Dowel-Type Fastener Design	
		Bottom of Beam Stressed in Tension (Positive Bending)	Top of Beam Stressed in Tension (Negative Bending)	Ten. Face	Comp. Face		True	App-arent	Beam Stabi-lity				True	App-arent	Beam Stabi-lity			Top or Bottom Face	Side Face
		$F_{bx}^+$ (psi)	$F_{bx}^-$ (psi)	$F_{cLx}$ (psi)	$F_{vx}$ (psi)	$E_{x\ true}$ ( $10^6$ psi)	$E_{x\ app}$ ( $10^6$ psi)	$E_{x\ min}$ ( $10^6$ psi)	$F_{by}$ (psi)	$F_{cLy}$ (psi)	$F_{vy}$ (psi)	$E_{y\ true}$ ( $10^6$ psi)	$E_{y\ app}$ ( $10^6$ psi)	$E_{y\ min}$ ( $10^6$ psi)	$F_t$ (psi)	$F_c$ (psi)	SG		
Power Preserved Glulam EWS 24F-V5M1/SP	SP/SP (B)	2,400	2,400	740	740	300	1.9	1.8	0.95	1,750	650	265	1.6	1.5	0.79	1,150	1,650	0.55	0.55
Wet-use factor		0.8		0.53		0.875	0.833			0.8	0.53	0.875	0.833			0.8	0.73	see NDS	

<sup>(1)</sup> The combinations in this table are intended primarily for members stressed in bending due to loads applied perpendicular to the wide faces of the laminations. Design values are tabulated, however, for loading both perpendicular and parallel to the wide faces of the laminations.

<sup>(2)</sup> The tabulated design values are for normal duration of loading. For other durations of loading, see the applicable building code. The tabulated design values are for dry conditions of use. For wet conditions of use, multiply the tabulated values by the wet-use factors shown at the bottom of the table.

<sup>(3)</sup> SP = Southern pine.

<sup>(4)</sup> The unbalanced (U) layout is intended primarily for simple-span applications and the balanced (B) layout is intended primarily for continuous or cantilevered applications.

<sup>(5)</sup> The values of  $F_{bx}$  are based on members 5-1/8 inches in width by 12 inches in depth by 21 feet in length. For members with a larger volume,  $F_{bx}$  shall be multiplied by a volume factor,  $C_v = (5.125/b)^{1/20} (12/d)^{1/20} (21/L)^{1/20}$ , where b is the beam width (in.), d is the beam depth (in.), and L is the beam length between the points of zero moment (ft).

<sup>(6)</sup> For non-prismatic members, members subject to impact or cyclic loading, or shear design of bending members at connections (NDS 3.4.3.3), the  $F_{vx}$  and  $F_{vy}$  values shall be multiplied by a factor of 0.72. The tabulated  $F_{vy}$  values are for timbers with laminations made from a single piece of lumber across the width or multiple pieces that have been edge bonded. For timber manufactured from multiple piece laminations (across width) that are not edge bonded, value shall be multiplied by 0.4 for members with 5, 7, or 9 laminations or by 0.5 for all other members.

<sup>(7)</sup> The tabulated E values include true E (also known as "shear-free E"), apparent E, and E for beam stability calculation (NDS 3.3.3.8). For calculating beam deflections, the tabulated  $E_{app}$  values shall be used unless the shear deflection is determined in addition to bending deflection based on the tabulated  $E_{true}$ . The axial modulus of elasticity,  $E_{axial}$  and  $E_{axial\ min}$ , shall be equal to the tabulated  $E_{y\ true}$  and  $E_{y\ min}$  values.

<sup>(8)</sup> The values of  $F_{by}$  are based on members 12 inches in depth. For depths less than 12 inches,  $F_{by}$  shall be permitted to be increased by multiplying by the size factor,  $(12/d)^{1/9}$ , where d is the beam depth in inches. When d is less than 3 inches, use the size adjustment factor for 3 inches.

Table 2. Design Values for Power Preserved Columns for Normal Duration of Load <sup>(1)</sup>

Combination Symbol	Species <sup>(2)</sup>	Grade	All Loading				Axially Loaded			Bending about Y-Y Axis				Bending about X-X Axis		Fasteners  Specific Gravity for Dowel-Type Fastener Design	
			Modulus of Elasticity <sup>(3)</sup>			Compression Perpendicular to Grain	Tension Parallel to Grain	Compression Parallel to Grain		Loaded Parallel to Wide Faces of Laminations			Loaded Perpendicular to Wide Faces of Laminations				
			E <sub>axial</sub> (10 <sup>6</sup> psi)	0.95 E <sub>axial</sub> (10 <sup>6</sup> psi)	E <sub>axial min</sub> (10 <sup>6</sup> psi)			F <sub>cL</sub> (psi)	2 or More Lams	4 or More Lams	2 or 3 Lams	Bending <sup>(4)</sup>			Shear Parallel to Grain <sup>(5,6)</sup>		Bending <sup>(7)</sup> 2 Lams to 15 in. Deep <sup>(8)</sup>
						F <sub>t</sub> (psi)	F <sub>c</sub> (psi)					F <sub>c</sub> (psi)	4 or More Lams	3 Lams			
Wet-use factors			0.833			0.53	0.8	0.73			0.8			0.875	0.8	0.875	see NDS
Power Preserved Glulam EWS 50	SP	N1D14	2.0	1.9	1.00	740	1,550	2,300	1,700	2,300	2,100	1,750	260	2,100 <sup>(8)</sup>	300	0.55	
Wet-use factors			0.833			0.53	0.8	0.73			0.8			0.875	0.8	0.875	see NDS

<sup>(1)</sup> The tabulated design values are for normal duration of loading. For other durations of loading, see applicable building code. The tabulated design values are for dry conditions of use. For wet conditions of use, multiply the tabulated values by the factors shown at the bottom of the table.

<sup>(2)</sup> SP = South pine.

<sup>(3)</sup> The tabulated E values include axial modulus of elasticity (E<sub>axial</sub>), 0.95 E<sub>axial</sub>, and E for column stability calculation (E<sub>axial min</sub>, NDS 3.7.1). For calculating column deflections due to lateral loads, the tabulated 0.95 E<sub>axial</sub> values shall be used unless the shear deflection is determined in addition to bending deflection based on the tabulated E<sub>axial</sub>.

<sup>(4)</sup> The values of F<sub>by</sub> are based on members 12 inches in depth. For depths less than 12 inches, F<sub>by</sub> shall be permitted to be increased by multiplying by the size factor, (12/d)<sup>1/8</sup>, where d is the beam depth in inches. When d is less than 3 inches, use the size adjustment factor for 3 inches.

<sup>(5)</sup> For non-prismatic members, notched members, members subject to impact or cyclic loading, or shear design of bending members at connections (NDS 3.4.3.3), the tabulated F<sub>vx</sub> and F<sub>vy</sub> values shall be multiplied by 0.72.

<sup>(6)</sup> The tabulated F<sub>vy</sub> values are for members of 4 or more lams. The tabulated F<sub>vy</sub> values shall be multiplied by a factor of 0.95 for 3 lams and 0.84 for 2 lams. For members with 5, 7, or 9 lams manufactured from multiple-piece lams with unbonded edge joints, the tabulated F<sub>vy</sub> values shall be multiplied by a factor of 0.4. For all other members manufactured from multiple-piece lams with unbonded edge joints, the tabulated F<sub>vy</sub> values shall be multiplied by a factor of 0.5. This adjustment shall be cumulative with the adjustment specified in Footnote 5.

<sup>(7)</sup> The values of F<sub>bx</sub> are based on members 5-1/8 inches in width by 12 inches in depth by 21 feet in length. For members with a larger volume, F<sub>bx</sub> shall be multiplied by a volume factor, C<sub>v</sub> = (5.125/b)<sup>1/20</sup> (12/d)<sup>1/20</sup> (21/L)<sup>1/20</sup>, where b is the beam width (in.), d is the beam depth (in.), and L is the beam length between the points of zero moment (ft).

<sup>(8)</sup> When the member depth is greater than 15 inches, the tabulated F<sub>bx</sub> values shall be multiplied by a factor of 0.88. This factor shall be cumulative with the volume factor, C<sub>v</sub>, specified in Footnote 7.

*APA – The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION**  
**HEADQUARTERS**

7011 So. 19<sup>th</sup> St. ▪ Tacoma, Washington 98466  
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: [www.apawood.org](http://www.apawood.org)

**PRODUCT SUPPORT HELP DESK**  
(253) 620-7400 ▪ *E-mail Address:* help@apawood.org

**DISCLAIMER**

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.