

Roseburg RFPI[®] Series I-Joists
Roseburg Forest Products Company

PR-L259C

Issued November 27, 2020

Products: Roseburg RFPI Series I-Joists
Roseburg Forest Products Company, 4500 Riddle Bypass Road, Riddle, Oregon 97469
(800) 347-7260
www.roseburg.com

1. Basis of the product report:
 - 2015 National Building Code of Canada (NBCC): Clause 1.2.1.1 of Division A, and Clauses 4.1, 4.3.1.1, and 9.23.4.2 of Division B
 - CAN/CSA O86-14 (reprinted May 2016) Engineering Design in Wood
 - ASTM D5055-13e1 recognized by CAN/CSA O86-14
 - Performance Standard for APA EWS I-Joists, PRI-400
 - APA Reports T2000P-14, T2001P-64, T2002P-57, T2002P-62A, T2003P-15, T2003P-20, T2003P-67, T2005P-101C, T2006P-04, T2006P-76A, T2008P-11, T2008P-75, T2009P-33, T2009P-42, T2009P-48, T2009P-50, T2010P-35, T2010P-57, T2011P-51, T2011P-52, T2012P-31, T2013P-22, T2013P-24A, T2015L-05B, T2015P-06, T2017L-25, and T2018P-30, and other qualification data
2. Product description:

All RFPI series I-joists, as described in Table 1, are made with laminated veneer lumber (LVL) flanges with the exception of RFPI-40S, RFPI-60S and RFPI-80S, which are made of lumber flanges, and OSB webs in accordance with the in-plant manufacturing standard approved by APA.
3. Design properties:

Tables 2 and 3 list the Limit States Design (LSD) properties for RFPI series I-joists. Table 4 shows web stiffener information. Design span information for RFPI series I-joists shall be in accordance with the recommendations provided by the manufacturer (www.roseburg.com).
4. Product installation:

RFPI Series I-Joists shall be installed in accordance with the recommendations provided by the manufacturer (see link above). Permissible web holes and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above), APA Product Report PR-S259, or Table A-9.10.3.1.-B or the calculation method specified in Appendix D-2.3 of NBCC.
6. Limitations:
 - a) RFPI Series I-Joists shall be designed in accordance with the code using the design properties specified in this report.
 - b) RFPI Series I-Joists are limited to dry service conditions as defined in CSA O86, at which the average equilibrium moisture content of solid-sawn lumber over a year is 15 percent or less and does not exceed 19 percent.
 - c) All RFPI Series I-Joists are produced at Roseburg Forest Products Company facility in Riddle, Oregon under a quality assurance program audited by APA.
 - d) RFPI-40S, RFPI-60S and RFPI-80S are also produced at the EACOM Timber Corporation facility in Sault Ste. Marie, Ontario under a quality assurance program audited by APA.

- e) RFPI-40S and RFPI-60S are also produced at the IB EWP Inc.'s facility in Pohénégamook, Quebec under a quality assurance program audited by APA.
- f) This report is subject to re-examination in one year.

7. Identification:

The RFPI Series prefabricated wood I-joists described in this report are identified by a label bearing the manufacturer's name (Roseburg Forest Products Company) and/or trademark, the APA assigned plant number (1053 for Roseburg Forest Products, Riddle, Oregon, 1058 for EACOM, Sault Ste. Marie, Ontario, and 1135 for IB EWP Inc., Pohénégamook, Quebec), the I-joist depth and series, the APA logo, the report number PR-L259, and a means of identifying the date of manufacture. RFPI-40, RFPI-70, and RFPI-90 are permitted to be labelled as onCENTER® BLI 400, BLI 700, and BLI 900, respectively.

Table 1. Description of Roseburg Forest Products RFPI Series of I-Joists ^(a)

Joist Series	Joist Depth, mm (in.)	Flange				Web	
		Material	G ^(b)	Dimension		Material	Thickness, mm (in.)
				Depth, mm (in.)	Width, mm (in.)		
RFPI-20	241 – 356 (9-1/2 – 14)	LVL	0.50	35 (1-3/8)	44 (1-3/4)	OSB	9.5 (3/8)
RFPI-40S	241 – 406 (9-1/2 – 16)	Proprietary SPF/DFL (MSR)	0.42 ^(c)	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
RFPI-400	241 – 406 (9-1/2 – 16)	LVL	0.50	35 (1-3/8)	52 (2-1/16)	OSB	9.5 (3/8)
RFPI-40	241 – 406 (9-1/2 – 16)	LVL	0.50	35 (1-3/8)	59 (2-5/16)	OSB	9.5 (3/8)
RFPI-60S	241 – 406 (9-1/2 – 16)	Proprietary SPF/DFL (MSR)	0.46 ^(c)	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
RFPI-70	241 – 406 (9-1/2 – 16)	LVL	0.50	38 (1-1/2)	59 (2-5/16)	OSB	9.5 (3/8)
RFPI-80S	302 – 406 (11-7/8 – 16)	MSR SPF/DFL	0.46 ^(c)	38 (1-1/2)	89 (3-1/2)	OSB	9.5 (3/8)
RFPI-90	241 – 406 (9-1/2 – 16)	LVL	0.50	38 (1-1/2)	89 (3-1/2)	OSB	11.1 (7/16)
RFPI-700	457 – 610 (18 – 24)	LVL	0.50	38 (1-1/2)	59 (2-5/16)	OSB	11.1 (7/16)
RFPI-900	457 – 610 (18 – 24)	LVL	0.50	38 (1-1/2)	89 (3-1/2)	OSB	11.1 (7/16)

- ^(a) Referenced dimensions are nominal. Tolerances are as specified in the plant quality manual.
- ^(b) Specific gravity of flanges for use in diaphragm design based on oven-dry weight and oven-dry volume for lumber flanges or equivalent specific gravity for LVL flanges.
- ^(c) The specific gravity value is permitted to be increased to 0.49 if the flange species is Douglas fir-Larch.

Table 2. Factored Resistances of RFPI Series I-Joists (a)

Joist Depth, mm (in.)	Joist Series	Permitted to Be Labelled as	EI ^(b) , 10 ⁹ N-mm ² (10 ⁶ lbf-in. ²)	M _r ^(c) , N-m (lbf-ft)	V _r ^(d) , N (lbf)	VLC _r ^(e) , kN/m (plf)	K ^(f) , 10 ⁶ N (10 ⁶ lbf)
241 (9-1/2)	RFPI-20	BLI 400	473 (165)	6,360 (4,690)	8,565 (1,926)	48.7 (3,336)	22.0 (4.94)
	RFPI-40S		554 (193)	6,000 (4,426)	7,865 (1,768)	48.7 (3,336)	22.0 (4.94)
	RFPI-400		554 (193)	7,545 (5,563)	8,565 (1,926)	48.7 (3,336)	22.0 (4.94)
	RFPI-40	BLI 700	617 (215)	8,480 (6,254)	9,340 (2,099)	48.7 (3,336)	22.0 (4.94)
	RFPI-60S		663 (231)	7,650 (5,644)	7,865 (1,768)	48.7 (3,336)	22.0 (4.94)
	RFPI-70		763 (266)	11,570 (8,532)	9,340 (2,099)	48.7 (3,336)	22.0 (4.94)
	RFPI-90		1,142 (398)	17,655 (13,023)	13,270 (2,983)	48.7 (3,336)	22.0 (4.94)
302 (11-7/8)	RFPI-20	BLI 400	812 (283)	8,210 (6,054)	9,970 (2,241)	48.7 (3,336)	27.5 (6.18)
	RFPI-40S		947 (330)	7,710 (5,686)	9,970 (2,241)	48.7 (3,336)	27.5 (6.18)
	RFPI-400		947 (330)	9,730 (7,177)	10,390 (2,336)	48.7 (3,336)	27.5 (6.18)
	RFPI-40	BLI 700	1,050 (366)	10,950 (8,075)	10,880 (2,447)	48.7 (3,336)	27.5 (6.18)
	RFPI-60S		1,136 (396)	9,910 (7,311)	9,970 (2,241)	48.7 (3,336)	27.5 (6.18)
	RFPI-70		1,306 (455)	14,985 (11,052)	10,880 (2,447)	48.7 (3,336)	27.5 (6.18)
	RFPI-80S		1,570 (547)	15,715 (11,593)	11,165 (2,510)	48.7 (3,336)	27.5 (6.18)
	RFPI-90	BLI 900	1,940 (676)	22,875 (16,873)	14,395 (3,236)	48.7 (3,336)	27.5 (6.18)
356 (14)	RFPI-20	BLI 400	1,205 (420)	9,765 (7,202)	11,305 (2,541)	48.7 (3,336)	32.4 (7.28)
	RFPI-40S		1,383 (482)	9,630 (7,102)	12,005 (2,699)	48.7 (3,336)	32.4 (7.28)
	RFPI-400		1,395 (486)	11,590 (8,549)	12,005 (2,699)	48.7 (3,336)	32.4 (7.28)
	RFPI-40	BLI 700	1,550 (540)	13,045 (9,622)	12,425 (2,794)	48.7 (3,336)	32.4 (7.28)
	RFPI-60S		1,676 (584)	11,935 (8,803)	12,005 (2,699)	48.7 (3,336)	32.4 (7.28)
	RFPI-70		1,928 (672)	17,870 (13,181)	12,425 (2,794)	48.7 (3,336)	32.4 (7.28)
	RFPI-80S		2,301 (802)	18,920 (13,954)	12,885 (2,896)	48.7 (3,336)	32.4 (7.28)
	RFPI-90	BLI 900	2,847 (992)	27,285 (20,125)	15,410 (3,465)	48.7 (3,336)	32.4 (7.28)
406 (16)	RFPI-40S	BLI 400	1,885 (657)	11,160 (8,233)	13,830 (3,109)	48.7 (3,336)	37.0 (8.32)
	RFPI-400		1,908 (665)	13,260 (9,780)	13,830 (3,109)	48.7 (3,336)	37.0 (8.32)
	RFPI-40		2,115 (737)	14,915 (11,002)	13,830 (3,109)	48.7 (3,336)	37.0 (8.32)
	RFPI-60S	BLI 700	2,293 (799)	13,840 (10,207)	13,830 (3,109)	48.7 (3,336)	37.0 (8.32)
	RFPI-70		2,634 (918)	20,475 (15,102)	13,830 (3,109)	48.7 (3,336)	37.0 (8.32)
	RFPI-80S		3,134 (1,092)	21,940 (16,183)	14,535 (3,267)	48.7 (3,336)	37.0 (8.32)
	RFPI-90		3,874 (1,350)	31,265 (23,060)	16,360 (3,678)	48.7 (3,336)	37.0 (8.32)

(Footnotes on the following page)

Table 2. Factored Resistances of RFPI Series I-Joists ^(a) (Continued)

Joist Depth, mm (in.)	Joist Series	Permitted to Be Labelled as	EI ^(b) , 10 ⁹ N-mm ² (10 ⁶ lbf-in. ²)	M _r ^(c) , N-m (lbf-ft)	V _r ^(d) , N (lbf)	VLC _r ^(e) , kN/m (plf)	K ^(f) , 10 ⁶ N (10 ⁶ lbf)
457 (18)	RFPI-700		3,573 (1,245)	23,565 (17,380)	18,080 (4,064)	53.6 (3,670)	50.4 (11.34)
	RFPI-900		5,306 (1,849)	36,260 (26,744)	20,255 (4,554)	53.6 (3,670)	50.4 (11.34)
508 (20)	RFPI-700		4,531 (1,579)	26,160 (19,293)	19,235 (4,325)	53.6 (3,670)	56.0 (12.60)
	RFPI-900		6,706 (2,337)	40,265 (29,696)	20,675 (4,648)	53.6 (3,670)	56.0 (12.60)
559 (22)	RFPI-700		5,610 (1,955)	28,730 (21,189)	20,605 (4,633)	43.8 (3,003)	61.6 (13.86)
	RFPI-900		8,282 (2,886)	44,230 (32,624)	21,135 (4,751)	43.8 (3,003)	61.6 (13.86)
610 (24)	RFPI-700		6,815 (2,375)	31,275 (23,069)	21,485 (4,830)	42.6 (2,919)	67.3 (15.12)
	RFPI-900		10,032 (3,496)	48,155 (35,518)	21,485 (4,830)	42.6 (2,919)	67.3 (15.12)

For Imperial: 1 mm = 0.0394 in., 1 N = 0.2248 lbf, 1 kN/m = 5.71 lbf/in.

- ^(a) All factored resistance values include the resistance factor specified in CSA O86. The tabulated values are for the standard term of load duration (K_D = 1.0). All values, except for EI, V_{Lr}, and K, are permitted to be adjusted for other load durations as permitted by the code.
- ^(b) Bending stiffness (EI) of the I-joist.
- ^(c) Factored moment resistance (M_r) of the I-joist.
- ^(d) Factored shear resistance (V_r) of the I-joist.
- ^(e) Factored uniform vertical load resistance (VLC_r) of the I-joist.
- ^(f) Coefficient of shear deflection (K). For calculating uniform load and center-point load deflections of the I-joists in a simple-span application, use Eqs. 1 and 2.

$$\text{Uniform Load: } \delta = \frac{5 \omega L^4}{384 EI} + \frac{\omega L^2}{K} \quad [1]$$

$$\text{Center-Point Load: } \delta = \frac{PL^3}{48 EI} + \frac{2 PL}{K} \quad [2]$$

where δ = calculated deflection (mm or in.), ω = unfactored uniform load (kN/mm or lbf/in.),
 P = unfactored concentrated load (kN or lbf), L = design span (mm or in.),
 EI = bending stiffness of the I-joist (kN-mm² or lbf-in.²), and K = coefficient of shear deflection (kN or lbf).

Table 3. Additional Factored Resistances of RFPI Series I-Joists (a,b,c)

Joist Depth, mm (in.)	Joist Series	Permitted to Be Labelled as	Factored End Reactions, N (lbf)						Factored Intermediate Reactions, N (lbf)				Web Bearing Stiffener
			45 mm (1-3/4 in.) Bearing		89 mm (3-1/2 in.) Bearing		102 mm (4 in.) Bearing		89 mm (3-1/2 in.) Bearing		133 mm (5-1/4 in.) Bearing		
			No B.S.	B.S.	No B.S.	B.S.	No B.S.	B.S.	No B.S.	B.S.	No B.S.	B.S.	
241 (9-1/2)	RFPI-20		6,390 (1,436)	8,075 (1,815)	8,075 (1,815)	8,425 (1,894)	8,565 (1,926)	8,565 (1,926)	12,460 (2,802)	13,165 (2,960)	14,040 (3,157)	16,150 (3,630)	4-8d
	RFPI-40S		7,580 (1,705)	7,865 (1,768)	7,795 (1,752)	7,865 (1,768)	7,865 (1,768)	7,865 (1,768)	15,165 (3,409)	15,725 (3,536)	15,725 (3,536)	15,725 (3,536)	4-8d
	RFPI-400		7,195 (1,618)	8,565 (1,926)	8,250 (1,855)	8,565 (1,926)	8,565 (1,926)	8,565 (1,926)	15,095 (3,394)	15,795 (3,551)	16,150 (3,630)	17,130 (3,851)	4-8d
	RFPI-40	BLI 400	7,580 (1,705)	8,565 (1,926)	8,915 (2,005)	9,160 (2,060)	9,340 (2,099)	9,340 (2,099)	15,795 (3,551)	17,550 (3,946)	17,905 (4,025)	18,605 (4,183)	4-8d
	RFPI-60S		7,580 (1,705)	7,865 (1,768)	7,795 (1,752)	7,865 (1,768)	7,865 (1,768)	7,865 (1,768)	15,165 (3,409)	15,725 (3,536)	15,725 (3,536)	15,725 (3,536)	4-8d
	RFPI-70	BLI 700	7,865 (1,768)	9,340 (2,099)	8,985 (2,020)	9,340 (2,099)	9,340 (2,099)	9,340 (2,099)	16,395 (3,686)	17,550 (3,946)	17,905 (4,025)	18,605 (4,183)	4-8d
	RFPI-90		9,340 (2,099)	11,130 (2,502)	11,340 (2,549)	12,780 (2,873)	11,935 (2,683)	13,270 (2,983)	21,205 (4,767)	24,185 (5,438)	24,185 (5,438)	24,395 (5,485)	4-10d
302 (11-7/8)	RFPI-20		6,670 (1,499)	8,600 (1,934)	9,230 (2,076)	9,655 (2,170)	9,970 (2,241)	9,970 (2,241)	13,585 (3,054)	14,285 (3,212)	14,990 (3,370)	17,095 (3,843)	4-8d
	RFPI-40S		8,425 (1,894)	9,410 (2,115)	9,620 (2,162)	9,830 (2,210)	9,970 (2,241)	9,970 (2,241)	17,550 (3,946)	18,430 (4,143)	18,675 (4,199)	19,940 (4,483)	4-8d
	RFPI-400		7,370 (1,657)	8,880 (1,997)	9,690 (2,178)	10,040 (2,257)	10,390 (2,336)	10,390 (2,336)	15,795 (3,551)	16,500 (3,709)	16,500 (3,709)	18,605 (4,183)	4-8d
	RFPI-40	BLI 400	8,425 (1,894)	9,830 (2,210)	10,320 (2,320)	10,635 (2,391)	10,880 (2,447)	10,880 (2,447)	17,475 (3,929)	18,430 (4,143)	18,675 (4,199)	20,150 (4,530)	4-8d
	RFPI-60S		8,425 (1,894)	9,410 (2,115)	9,620 (2,162)	9,830 (2,210)	9,970 (2,241)	9,970 (2,241)	17,550 (3,946)	18,430 (4,143)	18,675 (4,199)	19,940 (4,483)	4-8d
	RFPI-70	BLI 700	8,425 (1,894)	10,320 (2,320)	10,320 (2,320)	10,740 (2,415)	10,880 (2,447)	10,880 (2,447)	17,550 (3,946)	18,430 (4,143)	18,675 (4,199)	20,150 (4,530)	4-8d
	RFPI-80S		8,985 (2,020)	11,165 (2,510)	10,460 (2,352)	11,165 (2,510)	10,880 (2,447)	11,165 (2,510)	19,730 (4,435)	22,325 (5,019)	21,765 (4,893)	22,325 (5,019)	4-10d
RFPI-90	BLI 900	9,830 (2,210)	12,250 (2,754)	12,460 (2,802)	13,900 (3,125)	13,235 (2,975)	14,395 (3,236)	23,555 (5,296)	24,395 (5,485)	24,395 (5,485)	25,800 (5,801)	4-10d	
356 (14)	RFPI-20		6,670 (1,499)	9,055 (2,036)	9,935 (2,233)	10,775 (2,423)	10,880 (2,447)	11,305 (2,541)	13,585 (3,054)	14,285 (3,212)	14,990 (3,370)	17,095 (3,843)	4-8d
	RFPI-40S		8,425 (1,894)	10,740 (2,415)	10,320 (2,320)	11,725 (2,636)	10,880 (2,447)	12,005 (2,699)	17,550 (3,946)	19,235 (4,325)	19,340 (4,349)	21,415 (4,814)	4-8d
	RFPI-400		7,370 (1,657)	9,160 (2,060)	10,075 (2,265)	11,375 (2,557)	10,880 (2,447)	12,005 (2,699)	15,795 (3,551)	16,500 (3,709)	16,500 (3,709)	18,605 (4,183)	4-8d
	RFPI-40	BLI 400	8,425 (1,894)	10,950 (2,462)	10,320 (2,320)	12,075 (2,715)	10,880 (2,447)	12,425 (2,794)	17,550 (3,946)	19,235 (4,325)	19,340 (4,349)	21,520 (4,838)	4-8d
	RFPI-60S		8,425 (1,894)	10,740 (2,415)	10,320 (2,320)	11,725 (2,636)	10,880 (2,447)	12,005 (2,699)	17,550 (3,946)	19,235 (4,325)	19,340 (4,349)	21,415 (4,814)	4-8d
	RFPI-70	BLI 700	8,425 (1,894)	11,165 (2,510)	10,320 (2,320)	12,145 (2,731)	10,880 (2,447)	12,425 (2,794)	17,550 (3,946)	19,235 (4,325)	19,340 (4,349)	21,520 (4,838)	4-8d

(Footnotes on the following page)

Table 3. Additional Factored Resistances of RFPI Series I-Joists ^(a,b,c) (Continued)

Joist Depth, mm (in.)	Joist Series	Permitted to Be Labelled as	Factored End Reactions, N (lbf)						Factored Intermediate Reactions, N (lbf)				Web Bearing Stiffener Nails
			45 mm (1-3/4 in.) Bearing		89 mm (3-1/2 in.) Bearing		102 mm (4 in.) Bearing		89 mm (3-1/2 in.) Bearing		133 mm (5-1/4 in.) Bearing		
			No B.S.	B.S.	No B.S.	B.S.	No B.S.	B.S.	No B.S.	B.S.	No B.S.	B.S.	
356 (14)	RFPI-80S		8,985 (2,020)	12,285 (2,762)	10,460 (2,352)	12,745 (2,865)	10,880 (2,447)	12,885 (2,896)	21,205 (4,767)	23,590 (5,303)	22,535 (5,067)	25,275 (5,682)	4-10d
	RFPI-90	BLI 900	9,830 (2,210)	13,235 (2,975)	12,460 (2,802)	14,920 (3,354)	13,235 (2,975)	15,410 (3,465)	23,555 (5,296)	24,575 (5,524)	24,575 (5,524)	27,030 (6,077)	4-10d
406 (16)	RFPI-40S		8,425 (1,894)	12,005 (2,699)	10,320 (2,320)	13,410 (3,015)	10,880 (2,447)	13,830 (3,109)	17,550 (3,946)	20,010 (4,498)	20,010 (4,498)	22,820 (5,130)	4-8d
	RFPI-400		7,370 (1,657)	9,410 (2,115)	10,075 (2,265)	12,850 (2,889)	10,880 (2,447)	13,830 (3,109)	15,795 (3,551)	16,500 (3,709)	16,500 (3,709)	18,605 (4,183)	4-8d
	RFPI-40	BLI 400	8,425 (1,894)	12,005 (2,699)	10,320 (2,320)	13,410 (3,015)	10,880 (2,447)	13,830 (3,109)	17,550 (3,946)	20,010 (4,498)	20,010 (4,498)	22,820 (5,130)	4-8d
	RFPI-60S		8,425 (1,894)	12,005 (2,699)	10,320 (2,320)	13,410 (3,015)	10,880 (2,447)	13,830 (3,109)	17,550 (3,946)	20,010 (4,498)	20,010 (4,498)	22,820 (5,130)	4-8d
	RFPI-70	BLI 700	8,425 (1,894)	12,005 (2,699)	10,320 (2,320)	13,410 (3,015)	10,880 (2,447)	13,830 (3,109)	17,550 (3,946)	20,010 (4,498)	20,010 (4,498)	22,820 (5,130)	4-8d
	RFPI-80S		8,985 (2,020)	13,340 (2,999)	10,460 (2,352)	14,250 (3,204)	10,880 (2,447)	14,535 (3,267)	21,205 (4,767)	24,750 (5,564)	23,240 (5,225)	28,085 (6,314)	4-10d
	RFPI-90	BLI 900	9,830 (2,210)	14,215 (3,196)	12,460 (2,802)	15,865 (3,567)	13,235 (2,975)	16,360 (3,678)	23,555 (5,296)	24,750 (5,564)	24,750 (5,564)	28,260 (6,353)	4-10d
457 (18)	RFPI-700		7,900 (1,776)	15,445 (3,473)	11,585 (2,604)	18,080 (4,064)	12,635 (2,841)	18,080 (4,064)	19,270 (4,333)	28,435 (6,393)	21,240 (4,775)	31,420 (7,063)	8-8d
	RFPI-900		10,355 (2,328)	18,045 (4,057)	12,390 (2,786)	20,255 (4,554)	12,990 (2,920)	20,255 (4,554)	21,060 (4,735)	35,875 (8,066)	24,395 (5,485)	40,090 (9,013)	8-16d
508 (20)	RFPI-700		7,655 (1,720)	16,150 (3,630)	11,130 (2,502)	19,235 (4,325)	12,110 (2,723)	19,235 (4,325)	19,270 (4,333)	28,435 (6,393)	21,240 (4,775)	31,420 (7,063)	8-8d
	RFPI-900		9,480 (2,131)	18,710 (4,206)	11,935 (2,683)	20,675 (4,648)	12,635 (2,841)	20,675 (4,648)	21,060 (4,735)	35,875 (8,066)	24,395 (5,485)	40,090 (9,013)	8-16d
559 (22)	RFPI-700		NA	16,850 (3,788)	NA	20,605 (4,633)	NA	20,605 (4,633)	NA	29,135 (6,550)	NA	32,330 (7,269)	10-8d
	RFPI-900		NA	19,340 (4,349)	NA	21,135 (4,751)	NA	21,135 (4,751)	NA	37,945 (8,531)	NA	42,265 (9,502)	10-16d
610 (24)	RFPI-700		NA	17,550 (3,946)	NA	21,485 (4,830)	NA	21,485 (4,830)	NA	29,135 (6,550)	NA	32,330 (7,269)	10-8d
	RFPI-900		NA	20,010 (4,498)	NA	21,485 (4,830)	NA	21,485 (4,830)	NA	37,945 (8,531)	NA	42,265 (9,502)	10-16d

For Imperial: 1 mm = 0.0394 in., 1 N = 0.2248 lbf

- (a) The tabulated values in Table 3 are for the standard term of load duration ($K_D = 1.0$). All values are permitted to be adjusted for other load durations as permitted by the code provided that the adjusted values do not exceed the factored compressive resistance perpendicular to grain (Q_c) of the bearing plate supporting the I-joist in accordance with CSA O86.
- (b) Interpolation between bearing lengths is permitted.
- (c) Bearing stiffeners shall be installed in accordance with the recommendations provided by the manufacturer and APA E715 CA.

Table 4. Minimum Dimensions for Web Stiffeners and Accompanying Nails

Joist Designation	Minimum Dimensions		
	Web Stiffener		Nails
	Thickness, mm (in.)	Width, mm (in.)	
RFPI-20	15 (19/32)	59 (2-5/16)	8d box – 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-40S	25 (1)	59 (2-5/16)	8d box - 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-400	19 (3/4)	59 (2-5/16)	8d box - 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-40	25 (1)	59 (2-5/16)	8d box - 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-60S	25 (1)	59 (2-5/16)	8d box - 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-70	25 (1)	59 (2-5/16)	8d box - 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-80S	38 (1-1/2)	59 (2-5/16)	10d box - 76 mm x 3.25 mm (3 in. x 0.128 in.)
RFPI-90	38 (1-1/2)	59 (2-5/16)	10d box - 76 mm x 3.25 mm (3 in. x 0.128 in.)
RFPI-700	22 (7/8)	89 (3-1/2)	8d box – 64 mm x 2.87 mm (2-1/2 in. x 0.113 in.)
RFPI-900	38 (1-1/2)	89 (3-1/2)	16d box – 89 mm x 3.4 mm (3-1/2 in. x 0.135 in.)

APA – *The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
 HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466
 Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
 (253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.